TECHNICAL DATA SHEET TM300 SERIES



Product	Bituminous geomembrane
Composition	Geocomposite
Main Function	Waterproofing

Property	Test Method Texel ES1		el ES1	Texel ES2		Texel ES3	
		Typical	Minimum	Typical	Minimum	Typical	Minimum
Physical							
Geocomposite Glass mat Non-woven geotextile Elastomeric SBS Sand Polyester	-	50 g/m² 200 g/m² 3800 g/m² 250 g/m² 15 g/m²		50 g/m² 250 g/m² 4300 g/m² 250 g/m² 15 g/m²		50 g/m² 300 g/m² 4800 g/m² 250 g/m² 15 g/m²	
Weight	ASTM D3776	4.20 kg/m ²	3.70 kg/m²	4.85 kg/m²	4.30 kg/m²	5.80 kg/m²	5.00 kg/m²
Thickness	ASTM D5199	3.50 mm	3.10 mm	4.00 mm	3.60 mm	4.80 mm	4.20 mm
Mechanical							
Tear strength (MD/CD)	ASTM D4073	750 / 500 N	563 / 375 N	825 / 700 N	619 / 525 N	950 / 850 N	713 / 638 N
Tensile strength (MD/CD)	ASTM D7275	22 / 18 kN/m	16.5 / 13.5 kn/m	27 / 24 kN/m	20.3 / 15 kN/m	33 / 29 kN/m	24.8 / 21.8 kN/m
ongation at break (MD/CD) ASTM D7275				60 / 45%			
Puncture resistance	ASTM D4833	450 N	405 N	530 N	477 N	570 N	513 N
Flexibility at low temperature	-20 / -15 °C						
Hydraulic							
Water vapor transmission rate	ASTM E96	< 6 x 10 ⁻¹⁴ m/s					
Gas permeability	$< 2 \times 10^{-14} \mathrm{m}^3/(\mathrm{m}^2 \cdot \mathrm{j} \cdot \mathrm{amt})$						
Dimensions							
Width	-	5.1 m	5.01 m	5.1 m	5.01 m	5.1 m	5.01 m
Length	-	100 m	99 m	80 m	79 m	65 m	64 m

This technical informations comes from the manufacturer and was transcribed by Texel. Texel TM300 ES4 also available on request.

Rolls must not be stored directly on the ground. They must be laid supported on concrete blocks, trestles or timber beams min 35cm/1.2 ft height, placed under the mandrel ends.

Revision: 2020-04-27

