TM700P SR SERIES

TECHNICAL DATASHEET

Geomembrane (GMB) type	Scrim reinforced (SR)		
Composition	Polyethylene		
Main function	Impermeabilisation		

Property	Method	TM706P SR BW	TM708P SR BW	TM712P SR BW	TM720P SR BG	TM720P SR WW	
Physical							
Appearance	-	4 layers laminated geocomposite					
Thickness	-	Black/White (BW)			Black/Gray (BG)	White/White (WW)	
Coating thickness	-	132 g/m ²	166 g/m ²	269 g/m ²	361 g/m ²	475 g/m ²	
Weight	-	0.15 mm (6 mils)	0.20 mm (8 mils)	0.30 mm (12 mils)	0.51 mm (20 mils)	0.51 mm (20 mils)	
Mechanical							
1" Tensile strength	ASTM D7003	105 N/cm	108 N/cm	133 N/cm	131 N/cm	161 N/cm	
Elongation at film break	ASTM D7003	500%	500%	578%	700%	760%	
Elongation at scrim break	ASTM D7003	-	15%	14%	20%	16%	
Grab tensile	ASTM D7004	333 N	356 N	445 N	512 N	636 N	
Trapezoid tear	ASTM D4533	200 N ⁽¹⁾	222 N	262 N	311 N ⁽¹⁾	378 N ⁽¹⁾	
Tongue tear	ASTM D5884	-	133 N ⁽²⁾	178 N ⁽²⁾	236 N	280 N ⁽²⁾	
CBR puncture resistance	ASTM D6241	-	890 N	1112 N	1246 N	1557 N	
Mullen burst	ASTM D751	345 kPa	538 kPa	690 kPa	827 kPa	1172 kPa	
Maximum use temperature	-	82°C					
Minimum use temperature	-	-57℃					
Water vapor transmission rate (WVTR)	ASTM E96 - B	0.293 g/(m ² ·day)	0.268 g/(m ² ·day)	0.161 g/(m ² ·day)	0.151 g/(m ² ·day) (3)	0.151 g/(m ² ·day)	
Perm	ASTM E96 - B	0.028 g/(m ² ·day·mm Hg)	0.026 g/(m ² ·day·mm Hg)	0.015 g/(m ² ·day·mm Hg)	0.015 g/(m ² ·day·mm Hg) (3)	0.0145 g/(m ² ·day·mm Hg)	
Dimensions			· · · · · · · · · · · · · · · · · · ·				
Width & length	-	Variable	Variable	Variable	Variable	Variable	

This technical informations comes from the manufacturer and was transcribed by Texel.

Properties are typical values

Texe)

¹⁻ Tests are an average of diagonal directions / 2 - Tests are an average of MD and CD / 3 - Methode A / 4 - Maximum roll weight 5000 lbs (2270 kg)