

TM700P SR SERIES

TECHNICAL DATASHEET

Geomembrane (GMB) type	Scrim reinforced (SR)
Composition	Polyethylene
Main function	Impermeabilisation

Property	Method	TM706P SR BW	TM708P SR BB	TM712P SR BW	TM720P SR BG	TM720P SR WW
Physical						
Appearance	-	4 layers laminated geocomposite				
Color*	-	Black/White (BW)	Black/Black (BB)	Black/White (BW)	Black/Gray (BG)	White/White (WW)
Coating thickness	-	132 g/m ²	166 g/m ²	269 g/m ²	361 g/m ²	475 g/m ²
Weight	-	0.15 mm (6 mils)	0.20 mm (8 mils)	0.30 mm (12 mils)	0.51 mm (20 mils)	0.51 mm (20 mils)
Mechanical						
1" Tensile strength	ASTM D7003	105 N/cm	108 N/cm	133 N/cm	131 N/cm	161 N/cm
Elongation at film break	ASTM D7003	500%	500%	578%	700%	760%
Elongation at scrim break	ASTM D7003	-	15%	14%	20%	16%
Grab tensile	ASTM D7004	333 N	356 N	445 N	512 N	636 N
Trapezoid tear	ASTM D4533	200 N ⁽¹⁾	222 N	262 N	311 N ⁽¹⁾	378 N ⁽¹⁾
Tongue tear	ASTM D5884	-	133 N ⁽²⁾	178 N ⁽²⁾	236 N	280 N ⁽²⁾
CBR puncture resistance	ASTM D6241	-	890 N	1112 N	1246 N	1557 N
Mullen burst	ASTM D751	345 kPa	538 kPa	690 kPa	827 kPa	1172 kPa
Maximum use temperature	-	82°C				
Minimum use temperature	-	-57°C				
Water vapor transmission rate (WVTR)	ASTM E96 - B	0.293 g/(m ² ·day)	0.268 g/(m ² ·day)	0.161 g/(m ² ·day)	0.151 g/(m ² ·day) ⁽³⁾	0.151 g/(m ² ·day)
Perm	ASTM E96 - B	0.028 g/(m ² ·day·mm Hg)	0.026 g/(m ² ·day·mm Hg)	0.015 g/(m ² ·day·mm Hg)	0.015 g/(m ² ·day·mm Hg) ⁽³⁾	0.0145 g/(m ² ·day·mm Hg)
Dimensions						
Width & length	-	Variable	Variable	Variable	Variable	Variable

This technical information comes from the manufacturer and was transcribed by Texel.

Properties are typical values

1- Tests are an average of diagonal directions / 2 - Tests are an average of MD and CD / 3 - Methode A / 4 - Maximum roll weight 5000 lbs (2270 kg)

*Other colors may be available, validate with our customer service.

Revision : 2021-04-19

Texel reserves the right to modify existing properties contingent on the evolution of technical knowledge. Each user is invited to verify if this document represents the most recent update. Texel offers no guarantee and assumes no responsibility regarding usage, installation and/or convenience of usage. Texel must be informed of all product defects or product nonconformity prior to installation. Responsibility is limited to replacement of non-compliant or defective product.