

TM800i-T SERIES

TECHNICAL DATASHEET

Geomembrane (GMB) type	Textured/textured (T)
Composition	Linear low density polyethylene (LLDPE)
Main function	Impermeabilisation

Property	Test Method	Unit	Frequency ⁽¹⁾	TM840i-T	TM860i-T	TM880i-T	TM8-100i-T
Physical							
Nominal thickness	-	mils	-	40.0	60.0	80.0	100.0
Thickness (min. avg.)	ASTM D5199	mils	Every roll	38.0	57.0	76.0	95.0
Lowest individual 8/10 values	ASTM D5594	mils	Every roll	36.0	54.0	72.0	90.0
Lowest individual 10/10 values	ASTM D5594	mils	Every roll	34.0	51.0	68.0	85.0
Asperity height (min. avg.)	ASTM D7466	mils	Every roll	16	16	16	16
Melt index-190/2.16 (max.)	ASTM D1238	g/10 min	1/batch	1.0	1.0	1.0	1.0
Sheet density ⁽²⁾	ASTM D792	g/cc	Every 10 rolls	≤ 0.939	≤ 0.939	≤ 0.939	≤ 0.939
Carbon black content ⁽³⁾	ASTM D4218	%	Every 2 rolls	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0	2.0 - 3.0
Carbon black dispersion	ASTM D5596	Category	Every 10 rolls	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2	Cat. 1 / Cat. 2
OIT - standard (avg.)	ASTM D3895	min	Formulation	100	100	100	100
Mechanical							
Strength at break ⁽⁴⁾	ASTM D6693	ppi	Every 2 rolls	100	132	176	220
Elongation at break ⁽⁴⁾	ASTM D6693	%	Every 2 rolls	250	400	400	400
2% Modulus (max.)	ASTM D5323	ppi	Formulation	2400	3600	4800	6000
Tear resistance ⁽⁴⁾	ASTM D1004	lbf	Every 5 rolls	25	37	50	60
Puncture resistance ⁽⁴⁾	ASTM D4833	lbf	Every 5 rolls	56	84	112	140
Dimensional stability ⁽⁴⁾	ASTM D1204	%	Certification	± 2	± 2	± 2	± 2
Multi-axial tensile (min.)	ASTM D5617	%	Formulation	30	30	30	30
Oven aging- % retained 90 jours STD OIT ⁽⁴⁾	ASTM D5721 ASTM D3895	%	Formulation	35	35	35	35
HP OIT ⁽⁴⁾	ASTM D5885	%		60	60	60	60
UV resistance-% retained 1600h HP-OIT ⁽⁴⁾	GRI -GM11 ASTM D5885	%	Formulation	35	35	35	35
Dimensions (may vary ± 1%)							
Width X length	-	ft	-	22.3 X 780	22.3 X 540	22.3 X 420	22.3 X 320

This technical information comes from the manufacturer and was transcribed by Texel. All values are nominal test results, except when otherwise specified.

1-Testing frequency based on standard roll dimensions and one batch is approximately 180,000 lb (or one railcar). / 2 - ASTM D1505 and ASTM D792 give the same results

3 - ASTM D1603 and ASTM D4218 give the same results / 4 - Minimum average value on the basis of 5 specimens each direction (MD & TD)

Texel reserves the right to modify existing properties contingent on the evolution of technical knowledge. Each user is invited to verify if this document represents the most recent update. Texel offers no guarantee and assumes no responsibility regarding usage, installation and/or convenience of usage. Texel must be informed of all product defects or product nonconformity prior to installation. Responsibility is limited to replacement of non-compliant or defective product.